# terradec

## TERRA-CLEAR

### **PRODUCT DESCRIPTION**

TERRADEC-CLEAR is a 1-component, 100% solids, medium viscosity, UV stable, hard-elastic polyure thane binder. It cures using che $mical cross-linking to produce a binder with excellent abrasion characteristics for long term wear protection. {\sf TERRA-CLEAR} has good and the second sec$ resistance to diluted acids, alkaline, water, and a number of other chemical compounds.

#### USE

TERRADEC-CLEAR can be used as a binder for quartz carpet floors where epoxy is expected to give UV related yellowing problems. Only possible with washed and fire-dried quartz.

#### **TECHNICAL DATA:**

TERRADEC-CLEAR	
Colour	Transmort
	Transparant
Density at 20°C	1,15 kg/dm³
Viscosity	± 3000 mPa.s
VOC-content	< 1%
Solid-particle content	100%
Ignition point	>200°C
Processing time	25-45 minutes (faster at a higher air humidity/temperature)
Drying at 20 °C and 65% RV	Foot traffic: after 6 hours
	Mechanically cured: after 1 day
	Chemically cured: after 7 days
Application temperature	10°C - 30°C
Substrate requirements	- sufficiently dry
	- free of loose particle, grease, dust, dirt
Dilution	n.a.
Cleaning	PMA – acetone - xylene
Usage	5%
Packaging	sets of 20kg
Storage	12 months (in sealed, original packaging, 10-25°C)

#### INSTALLATION Further information, check the installation instructions of quartz carpet or marble stone.

SAFETY Please, read carrefully the msds-file.

Sidec is not responsible for any errors on this pages

26/10/2021

# PRODUCT DATASHEET